



**United co. for projects  
& technical advices**

**UPTA C10**

<b>TECHNICAL DATA SHEET</b>	<b>DESCRIPTION &amp; APPLICATION</b>	Surface coated, very fine, Calcium Carbonate powder obtained from high purity, very white limestone with the highest technology. Used in several plastic applications such as PVC pipes, mould elements, Master patch, Cables industries, Rubbers and Leather industries, etc.																	
	<b>CHEMICAL ANALYSIS</b>	<table> <tr> <td>CaCO<sub>3</sub></td> <td align="right">99.20%</td> </tr> <tr> <td>MgCO<sub>3</sub></td> <td align="right">0.20%</td> </tr> <tr> <td>Fe<sub>2</sub>O<sub>3</sub></td> <td align="right">0.01%</td> </tr> <tr> <td>HCl insoluble content</td> <td align="right">0.20%</td> </tr> </table>	CaCO <sub>3</sub>	99.20%	MgCO <sub>3</sub>	0.20%	Fe <sub>2</sub> O <sub>3</sub>	0.01%	HCl insoluble content	0.20%									
	CaCO <sub>3</sub>	99.20%																	
	MgCO <sub>3</sub>	0.20%																	
Fe <sub>2</sub> O <sub>3</sub>	0.01%																		
HCl insoluble content	0.20%																		
<b>SPECIFICATION PRODUCTION DATA</b>	<table> <tr> <td>Fineness :</td> <td></td> </tr> <tr> <td>Residue on a 45 µm sieve</td> <td align="right">0.01%</td> </tr> <tr> <td>Top Cut (D97)</td> <td align="right">10 µm</td> </tr> <tr> <td>Mean Particle Size (d50)</td> <td align="right">2.5µm</td> </tr> <tr> <td>Particles volume under 2 µm</td> <td align="right">40 %</td> </tr> <tr> <td>Whiteness %</td> <td align="right">96.3 %</td> </tr> <tr> <td>Yellowness index</td> <td align="right">0.80 %</td> </tr> <tr> <td>Moisture ex works</td> <td align="right">0.20 %</td> </tr> <tr> <td>Hardness by Moh's</td> <td align="right">3 Moh's</td> </tr> </table>	Fineness :		Residue on a 45 µm sieve	0.01%	Top Cut (D97)	10 µm	Mean Particle Size (d50)	2.5µm	Particles volume under 2 µm	40 %	Whiteness %	96.3 %	Yellowness index	0.80 %	Moisture ex works	0.20 %	Hardness by Moh's	3 Moh's
Fineness :																			
Residue on a 45 µm sieve	0.01%																		
Top Cut (D97)	10 µm																		
Mean Particle Size (d50)	2.5µm																		
Particles volume under 2 µm	40 %																		
Whiteness %	96.3 %																		
Yellowness index	0.80 %																		
Moisture ex works	0.20 %																		
Hardness by Moh's	3 Moh's																		
<b>GENERAL PRODUCTION DATA</b>	<table> <tr> <td>Packed bulk density</td> <td align="right">1.1 g\ml</td> </tr> <tr> <td>PH value</td> <td align="right">9</td> </tr> <tr> <td>Oil absorption</td> <td align="right">16.5g\100g</td> </tr> <tr> <td>Stearic acid</td> <td align="right">1.00%</td> </tr> </table>	Packed bulk density	1.1 g\ml	PH value	9	Oil absorption	16.5g\100g	Stearic acid	1.00%										
Packed bulk density	1.1 g\ml																		
PH value	9																		
Oil absorption	16.5g\100g																		
Stearic acid	1.00%																		

**Particle Size Distribution**

The data in the Technical Data Sheet represents average values which are valid and reliable but not legally binding .UPTA will not be liable for any use of data, or any damages arising from the use of products for purposes not examined in detail. This Technical Data Sheet renders all previous versions

Add. / SECTION NO 35 MINERAL SECTOR BAYAD EL-ARAB Industrial Zone, Beni  
Suif City, Egypt

Email: [info@UPTAegypt.com](mailto:info@UPTAegypt.com) Tel 01022994404

Email: [info@UPTAegypt.com](mailto:info@UPTAegypt.com) Fax: 251715