


United co. for projects

& technical advices UPTA 25 Natural, very fine, CALCIUM CARBONATE powder obtained **DESCRIPTION & APPLICATION** from high purity, very white limestone with the highest technology. used in exterior emulsion paints, industrial paints, adhesive, solvent based and water based paints, paper and high gloss powder coatings ,etc CaCO3 **CHEMICAL ANALYSIS** 99.20% MqCO3 0.20% Fe2O3 0.01% HCl insoluble content 0.20% **SPECIFICATION PRODUCTION DATA** Fineness: Residue on a 45 µm sieve 0.20% Top cut (d97) 25µm Mean particle size (d50) 4µm Particles under 2µm 27% 96,2% whiteness Yellowness index 1.20% Moisture ex works 0.20% Hardness by Moh's 3 Moh's **GENRAL PRODUCTION DATA** bulk density 0.8 g/ml pH value 16.5g/100g Oil absorption



The data in the Technical Data Sheet represents average values which are valid and reliable but not legally binding.UPTA will not be liable for any use of data, or any damages arising from the use of products for purposes not examined in detail. This Technical Data Sheet renders all previous versions invalid.

Add. / SECTION NO 35 MINERAL SECTOR BAYAD EL-ARAB Industerial Zone, Beni Suif City, Egypt

Email: info@UPTAegypt.com

Tel 01022994404